



BLUE MOUNTAIN MINERALS

24599 Marble Quarry Road
Columbia, California 95310
209.533.0127
FAX 209.532.0972

Agricultural Dolomite

	weight %	
	Min	Max
Calcium Carbonate Equivalent (CCE)	101.3	107.0
Calcium (Ca)	23.2	27.5
Magnesium (Mg)	9.0	10.9
Calcium Carbonate (CaCO ₃)	57.8	68.6
Magnesium Carbonate (MgCO ₃)	31.4	37.7
Moisture	2.0	4.0

Ag Lime Score (Oregon) = 98.3

TYPICAL SCREEN ANALYSIS

Screen Mesh Size	Size in Inches	% Retained	Cumulative % Retained	% Passing
10	.073"	0.0	0.0	100.0
20	.034"	0.0	0.0	100.0
40	.015"	3.0	3.0	97.0
50	.011"	2.3	5.3	94.7
100	.0055"	11.8	17.1	82.9
120	.0037"	6.0	23.1	76.9
200	.0029"	24.3	47.4	52.6
325	.0017"	21.7	69.0	31.0
Pan		28.3	97.3	2.7

OMRI™
L i s t e d
Organic Materials Review Institute